




171000110480



中国认可  
国际互认  
检测  
TESTING  
CNAS L0358



2017苏质监验字480号

# 检 验 检 测 报 告

## TEST REPORT

No. : (2018)CJ-WT-T0028

产 品 名 称  
Product Name

防火板  
(热固性树脂浸渍纸高压装饰层积板)  
HPL

受 检 单 位  
Inspected Party

委 托 单 位  
Entrusting Party

常州市亚明木业有限公司Changzhou  
Yaming Wood Industry Co.,Ltd

生 产 单 位  
Manufacturer

常州市亚明木业有限公司Changzhou  
Yaming Wood Industry Co.,Ltd

检 验 类 别  
Test Kind

Entrusted test

常州市产品质量监督检验所

Changzhou Product Quality Inspection & Supervision Institute



常州市产品质量监督检验所  
Changzhou Product Quality Inspection & Supervision Institute

检 验 检 测 报 告  
TEST REPORT

No. : (2018)CJ-WT-T0028

共 3 页 第 1 页

产品名称 Product Name	防火板 (热固性树脂浸渍纸高压装饰层积板) HPL		商标 Trademark	武亚	
生产日期/批号 Production Date/Batch No.	_____/2018.01.20		规格型号 Model & Type	0.7mm	
受检单位/地址/电话/邮编 Inspected Party/Add/Tel/Zip	_____/_____/_____/_____/_____/_____				
委托单位/地址/电话/邮编 Entrusting Party/Add/Tel/Zip	常州市亚明木业有限公司Changzhou Yaming Wood Industry Co.,Ltd/常州市经开区横林镇新横崔路55号No.55 New Hengcui Road Henglin Town Changzhou City/13815029218/213103				
生产单位/地址/电话/邮编 Manufacturer/Add/Tel/Zip	常州市亚明木业有限公司Changzhou Yaming Wood Industry Co.,Ltd/常州市经开区横林镇新横崔路55号No.55 New Hengcui Road Henglin Town Changzhou City/13815029218/213103				
样品数量 Sample Quantity	3片 Three pieces	样品编号 Samples list No.	Y(2018)CJ-WT-T0028		
样品状态 Sample Description	In good condition	样品到达日期 Samples Arrival Date	2018-01-22		
样品等级 Grade	____	检验检测类别 Test Kind	Entrusted test	检验检测日期 Test Date	2018-01-23~2018-02-02
检验检测和判定依据 Test Standard(s)	GB/T 7911-2013《热固性树脂浸渍纸高压装饰层积板(HPL)High-pressure decorative laminates-Sheets made from thermosetting resins》				
检验检测结论 Conclusion	结果见第2页。Test results are on page 2.				
检验检测地点 Address	Changzhou Product Quality Inspect and Supervision Institute, Henglin				
备注 Note	____				



批 准: 郑洪连

审 核: 殷俊

主 检: 张卫海

Approval:

郑洪连

Proofreader:

殷俊

Major tester:

张卫海

职 务: 授权签字人

post: Authorized signatory

# 检 验 检 测 结 果

## Test Results

No. : (2018)CJ-WT-T0028

共 3 页 第 2 页

序号 No.	检 验 检 测 项 目 Test Items	单 位 Unit	技 术 要 求 Standard Requirements	检 验 检 测 结 果 Test Results	单 项 评 价 Item Evaluate
1	耐磨性能 Abrasion resistance	—	2级 level 2	2级 level 2	合格 Qualified
2	耐沸水性能 Resistance to immersion in boiling water	质量增加百分率, % Mass increase	— ≤12.0	8.7	合格 Qualified
		厚度增加百分率, % Thickness increase	— ≤18.0	8.2	合格 Qualified
		外观 Appearance	— 等级不低于4级 Not worse than level 4	2级 Level 2	合格 Qualified
3	耐干热性能 Resistance to dry heat	外观光泽 Appearance gloss finish	— 等级不低于3级 Not worse than level 3	2级 Level 2	合格 Qualified
		其他 Other finishes	— 等级不低于4级 Not worse than level 4	1级 Level 1	合格 Qualified
4	耐湿热 Resistance to wet heat	—	等级不低于5级 Not worse than level 5	2级 Level 2	合格 Qualified
5	耐水蒸气 Resistance to water vapour	—	等级不低于4级 Not worse than level 4	2级 Level 2	合格 Qualified
6	抗大球冲击 (落球高度100cm) Resistance to impact by large-diameter ball (Drop height 100cm)	mm	—	1: 9 2: 9 3: 9 4: 9 5: 9	
7	耐划痕 Resistance to scratching	—	2级 Level 2	2级 Level 2	合格 Qualified
8	耐污染 Resistance to staining	丙酮(分析纯) Acetone (AR)	— 等级不低于4级 Not worse than level 4	1级 Level 1	合格 Qualified
		咖啡(每升水中含120g咖啡) Coffee (120 g of coffee per litre of water)	— 等级不低于4级 Not worse than level 4	1级 Level 1	合格 Qualified
		氢氧化钠25%(分析纯) Sodium hydroxide 25% solution (AR)	— 等级不低于4级 Not worse than level 4	1级 Level 1	合格 Qualified
		双氧水25%~30%(分析纯) Hydrogen peroxide 25%~30% solution (AR)	— 等级不低于4级 Not worse than level 4	1级 Level 1	合格 Qualified

# 检 验 检 测 结 果

## Test Results

No.: (2018)CJ-WT-T0028

共 3 页 第 3 页

序号 No.	检验检测项目 Test Items	单位 Unit	技 术 要 求 Standard Requirements	检验检测结果 Test Results	单项评价 Item Evaluate
8	耐污染 Resistance to staining	鞋油 Shoe polish	等级不低于4级 Not worse than level 4	1级 Level 1	合格 Qualified
		柠檬酸10% (食用) Citric acid 10% solution (edible)	等级不低于4级 Not worse than level 4	1级 Level 1	合格 Qualified
9	耐香烟灼烧 Resistance to cigarette burns	中华牌香烟 Chunghua cigarette	等级不低于3级 Not worse than level 3	2级 Level 2	合格 Qualified
		红塔山牌香烟 Hongtashan cigarette	等级不低于3级 Not worse than level 3	2级 Level 2	合格 Qualified
		牡丹牌香烟 Peony cigarette	等级不低于3级 Not worse than level 3	2级 Level 2	合格 Qualified
10	耐龟裂性能 Resistance to crazing	—	等级不低于4级 Not worse than level 4	5级 Level 5	合格 Qualified
11	耐开裂性能 Resistance to cracking under stress	—	等级不低于4级 Not worse than level 4	1级 Level 1	合格 Qualified
12	抗拉强度 Tensile Strength	MPa	—	76.265	/
13	滞燃性能 Reaction to fire	氧指数, % Oxygen index	B <sub>2</sub> 级 ≥27 Level B <sub>2</sub> ≥27	35.5	合格 Qualified
		水平燃烧 Horizontal burning	B <sub>2</sub> 级, 不低于HB40级 Level B <sub>2</sub> , not worse than level HB40	HB级 Level HB	合格 Qualified
		垂直燃烧 Vertical burning	B <sub>2</sub> 级, 不低于V-1级 Level B <sub>2</sub> , not worse than level V-1	V-1级 Level V-1	合格 Qualified
备注 Note					